

ABSTRACT OF THE DISCLOSURE

In the present invention, the concentration of dissolved oxygen in the resist stripping liquid is limited to 3 ppm or lower. Using the resist stripping
5 liquid having such a low dissolved oxygen concentration, resist residues are removed from a substrate containing copper and/or a copper alloy without causing the corrosion of copper.